



US007703375B1

(12) **United States Patent**  
**Scott et al.**

(10) **Patent No.:** **US 7,703,375 B1**  
(45) **Date of Patent:** **Apr. 27, 2010**

(54) **COMPOSITE ARMOR WITH A CELLULAR STRUCTURE**

(75) Inventors: **Brian R. Scott**, Middletown, DE (US);  
**Nabil F. Grace**, Rochester Hills, MI (US)

(73) Assignee: **Lawrence Technological University**,  
Southfield, MI (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **11/504,343**

(22) Filed: **Aug. 15, 2006**

(51) **Int. Cl.**  
**F41H 5/02** (2006.01)

(52) **U.S. Cl.** ..... **89/36.02**; 428/911; 89/915;  
89/917

(58) **Field of Classification Search** ..... 89/36.02;  
428/911

See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

3,616,115 A	10/1971	Klimmek	
3,649,426 A *	3/1972	Gates	428/68
3,828,699 A *	8/1974	Bowen	109/80
4,061,815 A *	12/1977	Poole, Jr.	428/215
4,186,648 A	2/1980	Clausen et al.	
4,198,454 A *	4/1980	Norton	428/117
4,251,579 A *	2/1981	Lee et al.	428/73
4,292,882 A *	10/1981	Clausen	89/36.02
4,307,140 A	12/1981	Davis	
4,404,889 A *	9/1983	Miguel	89/36.02
4,934,245 A *	6/1990	Musante et al.	89/36.02
4,953,442 A	9/1990	Bartuski	
4,969,386 A	11/1990	Sandstrom et al.	
4,989,493 A *	2/1991	Blommer et al.	89/36.02
5,032,466 A	7/1991	Cappa	
5,045,371 A	9/1991	Calkins	
5,114,772 A	5/1992	Vives et al.	

H1061 H *	6/1992	Rozner et al.	89/36.02
5,221,807 A	6/1993	Vives	
5,349,893 A	9/1994	Dunn	
H1434 H	5/1995	Cytron	
5,456,156 A	10/1995	Simple	
5,471,905 A *	12/1995	Martin	89/36.02
5,686,689 A	11/1997	Snedeker et al.	
5,733,643 A *	3/1998	Green	428/217
5,918,309 A *	7/1999	Bachner, Jr.	2/2.5
5,996,115 A	12/1999	Mazelsky	
6,009,789 A	1/2000	Lyons	
6,253,655 B1	7/2001	Lyons et al.	

(Continued)

**OTHER PUBLICATIONS**

Saito, Makoto, "Carbon Fiber Composites In The Japanese Civil Engineering Market—Conventional Uses And Developing Products" SAMPE Journal, vol. 38, No. 5, Sep./Oct. 2002, pp. 20-25.


(Continued)

*Primary Examiner*—Bret Hayes  
*Assistant Examiner*—Michael D David  
(74) *Attorney, Agent, or Firm*—Dickson Wright PLLC

(57) **ABSTRACT**

A composite armor **10** is provided with a cellular structure **12** having a plurality of composite inserts **14** arranged in openings **20** provided in the cellular structure **12**. A pair of laminate sheets are arranged on oppositely facing sides of the cellular structure **12** and covering the inserts **14**. The laminate sheets **26** and **28** are bonded to the structure **12** and the inserts **14** by an adhesive. The cellular structure **12** includes a plurality of fibers extending continuously throughout the cellular structure **12**.

**20 Claims, 6 Drawing Sheets**



# US 7,703,375 B1

Page 2

## U.S. PATENT DOCUMENTS

6,408,733	B1	6/2002	Perciballi						
6,408,734	B1	6/2002	Cohen						
6,497,966	B2	12/2002	Cohen						
6,532,857	B1	3/2003	Shih et al.						
6,601,497	B2*	8/2003	Ghiorse et al.	89/36.02		2002/0088340	A1*	7/2002	Chu et al. .... 89/36.02
6,679,157	B2*	1/2004	Chu et al.	89/36.02		2002/0094406	A1	7/2002	Cohen
6,681,679	B2*	1/2004	Vives et al.	89/36.17		2004/0020353	A1	2/2004	Ravid et al.
6,698,331	B1*	3/2004	Yu et al.	89/36.02		2005/0072294	A1	4/2005	Cohen
6,703,104	B1*	3/2004	Neal	428/118		2007/0034074	A1*	2/2007	Ravid et al. .... 89/36.02
6,792,843	B2*	9/2004	Mohr et al.	89/36.02		2007/0180982	A1*	8/2007	Dagher et al. .... 89/36.02
6,826,996	B2	12/2004	Strait			2007/0214951	A1*	9/2007	Swinson .... 89/36.04
6,860,186	B2	3/2005	Cohen			2007/0238379	A1*	10/2007	Bhatnagar et al. .... 442/135
6,892,623	B2	5/2005	Benyami et al.			2008/0119099	A1*	5/2008	Palley .... 442/134
6,895,851	B1*	5/2005	Adams et al.	89/36.02					
6,955,112	B1*	10/2005	Adams et al.	89/36.02					
7,150,217	B2*	12/2006	Kershaw	89/36.05					

## OTHER PUBLICATIONS

Nippon Steel Composite Co., Ltd. Brochure—FRP Grid FORCA TOWGRID (4 pages).  
Nefcom Corporation Brochure—FRP Reinforcing Bar NEFMAC (4 pages).

\* cited by examiner




Fig. 1




Fig. 2






Fig. 4




Fig. 5




Fig. 6



## COMPOSITE ARMOR WITH A CELLULAR STRUCTURE

### STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH

This invention was made with Government support under Agreement No. W911NF-04-2-0032 awarded by ARL. The Government has certain rights in the invention.

### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

The present invention relates generally to armor used for preventing the penetration of structures by projectiles. More specifically, the invention relates to an improved armor including a fiber grid having composite tiles retained in the grid that together provide overall support to the structure being protected while also improving the armor performance of each individual composite tile.

#### 2. Background of the Invention

Armor systems have been known to include thick metal as a skin of a structure being protected. For example, military vehicles have, for several years, included a thick metal plate on their exterior in order to reduce the likelihood of projectile penetration. Such thick metal armor systems while effective can also be extremely heavy and, as such, cause problems relating to vehicle speed, fuel consumption and vehicle assembly.

In some cases, these metal armor systems have been replaced with lighter weight armor systems made from composite materials having reinforced fibers made of, for example, Kevlar, S-2 glass, graphite, or high molecular weight polyethylene. Such armor systems have utilized these multiple layers of composite materials in order to achieve reduced overall weight, and provide sufficient structural properties, while preserving the ability of the armor to provide protection against penetration. For example, some known systems include the use of Kevlar in combination with two outer plates surrounding such Kevlar. Illustrative of such a composite armor system is disclosed in U.S. Pat. No. 4,186,648.

Also, armor systems using ceramic plates in connection with a grid are well known in the art as capable of providing protection against penetrating high speed projectiles while providing a reduction in the overall weight of the armor system. The ceramic plates have been known to have convex surfaces. U.S. Pat. No. 6,826,996 discloses convex plates inserted into a honeycomb grid. Upon impact by a projectile into such ceramic plates, it has been known that managing the propagation of cracks from the impacted plate to an adjacent plate is critical.

The prior art grids are made of steel, fiber, or composite materials and are used in connection with holding ceramic plates inserted into openings formed by such grid structures. For example, U.S. Pat. No. 5,456,156 discloses a grid structure made of metal strips. The openings have been known to be either blind openings, opening only to one side of the grid, or, through holes, open to both sides of the grid. The openings of such grids have been shaped in many different forms including, for example, squares, triangles, and hexagons. The grid structure is usually designed with a material having an effective acoustic impedance lower than the ceramic plates in order to reduce the propagation of damaging stresses to adjacent ceramic plates.

In order to manage the propagation of such stresses, prior art armor systems have used auxiliary layers of laminate sheet

material bonded to the front and the back of the grid structures. In some cases, only one laminate sheet has been bonded to either one of the front or the back of such grid structures. It has been known to make such laminate sheet material out of Kevlar. For example, U.S. Pat. No. 5,349,893 discloses a composite laminate sheet made of woven fiber in a resinous matrix. Such laminate sheet materials can be bonded to the grid structure with resins.

Illustrative of the prior art is U.S. Pat. No. 6,826,996 assigned to General Dynamics Land Systems, Inc. and Mofet Etzion Agricultural Cooperative Association Ltd. The '996 patent discloses a honeycomb grid structure having openings for receiving convex composite plates and a pair of preform sheets secured to both sides of the grid structure. The '996 patent discloses the honeycomb grid as made of material selected from the group consisting of stainless steel, aluminum, aramid sheet, fiber, or fabric.

Testing of such known armor systems having grid structures with composite inserts surrounded by preform sheets has revealed that the propagation of cracks and debris, created during impact, weakens the adjacent composite plates. The propagation of such cracks results from poorly designed grid structures failing to eliminate both crack propagation, debris, and stress wave propagation.

### SUMMARY OF THE INVENTION

It is an object of the present invention to provide a composite armor that will prevent the penetration of projectiles in a structure while also providing structural support to the same structure.

More specifically, an object of the invention is to provide a composite armor having a one-piece integrally formed composite cellular structure for retaining composite inserts, which in combination with resins and laminates, prevents projectiles from penetrating a structure.

Another object of the present invention is to provide a uniform one-piece composite cellular structure made of continuous fibers providing high tensile strength in order to radially confine composite inserts used in connection with such grid.

Further scope and applicability of the present invention will become apparent from the following detailed description, claims and drawings. However, it should be understood that the specific examples in the detailed description are given by way of illustration only, since various changes and modifications within the spirit and scope of the invention will become apparent to those skilled in the art.

### BRIEF DESCRIPTION OF THE DRAWINGS

The present invention will become more fully understood from the detailed description given here below, the appended claims, and the accompanying drawings in which:

FIG. 1 is a three dimensional exploded view of the subject invention;

FIG. 2 is a three dimensional exploded view of a portion of the subject invention;

FIG. 3 is a three dimensional exploded view of a portion of the subject invention taken along lines B-B in FIG. 1;

FIG. 4 is a three dimensional view of a cellular structure of the subject invention;

FIG. 5 is a plan view of a portion of the subject invention; and

FIG. 6 is a side view of a vehicle structure having the present invention used on at least a portion of such vehicle.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Referring now to the drawings, an armor system is shown in general at **10** in FIG. **1**. The armor system **10** includes a cellular structure **12** having a plurality of openings **20** adapted to receive composite inserts **14**. It should be appreciated that, although a plurality of openings for receiving inserts **14** are shown in this embodiment, it is possible to use any number of inserts **14** including, for example, only one insert **14**. The cellular structure **12** includes a first side **16** and a second side **18** having openings **20** extending between each of the first and second sides **16** and **18** and adapted to receive the inserts **14**. Although not shown, it is possible that the inserts **14** may be received in an opening **20** on only one side **16** of the cellular structure **12**. The composite inserts **14** include first and second ends **22** and **24**, respectively, and a perimeter portion **25**.

The armor system **10** further includes a pair of laminates **26** and **28** secured to the cellular structure **12** and the composite inserts **14**. The laminates **26**, **28** are secured with the use of a bonding material such as a resin which may also be used as a filler applied on the inserts **14** and, in some cases, around at least a portion of the perimeter portion **25**.

FIG. **2** shows only a portion of the armor system **10** including the cellular structure **12**, the composite inserts **14** and the laminate **26** comprised of four layers of lamina **30**, **32**, **34**, **36**. In this embodiment, the laminate **26** includes a pair of high modulus laminates **30** and **32** made of a carbon fiber reinforced polymer and an additional pair of laminates **34** and **36** made of a hybrid ductile fabric. The laminate is layered extending away from the cellular structure **12** in an alternating manner including the hybrid ductile fabric lamina **34**, high modulus lamina **30**, hybrid ductile fabric lamina **36** and high modulus lamina **32**, respectively. In the preferred embodiment, it has been found that materials having an acoustic impedance between  $0.7 \times 10^6$  and  $40 \times 10^6$  kg/m<sup>2</sup>, as measured in a direction parallel to a normal of the laminate sheets, are most effective. It should be appreciated that, although FIG. **2** only shows a portion of the armor system **10** having the laminate **26** extending from only the first side **16** of the cellular structure **12**, the armor system **10** may also include a similar laminate arrangement on the second side **18**.

Similar to FIG. **2**, FIG. **3** only shows a portion of another embodiment of the armor system **10** having the laminate **26** comprised of three layers of lamina extending from only the first side **16** of the cellular structure **12** and, by way of example, only one of the composite inserts **14**. In this embodiment, the laminate **26** includes a high modulus lamina **40**, a hybrid ductile fabric lamina **42** and a fiberglass lamina **44**, extending in a direction away from the cellular structure **12**, respectively. It should be appreciated that, although FIG. **3** only shows a portion of the armor system **10** having the laminate **26** extending from only the first side **16** of the cellular structure **12**, the armor system **10** may also include a similar laminate arrangement on the second side **18** of the cellular structure **12**.

FIG. **3** also shows, by way of example, one of the composite inserts **14** partially inserted into an opening **20** of the second side **18**. The composite inserts **14** can be made of the materials consisting of the group of ceramic, glass, metal matrix, and ceramic matrix composite. In this embodiment, the composite insert **14** includes first and second surfaces **22** and **24** perpendicular to an axis A of the openings **20**. In the preferred embodiment, the surfaces **22** and **24** have a minimum modulus of  $2.0 \times 10^{10}$  N/m<sup>2</sup> as measured in a through thickness orientation. Although not shown in FIG. **3**, it should be appreciated that the first and second surfaces **22** and **24**,

respectively, may have different surfaces including, for example, convex or concave surfaces. FIG. **3**, in this embodiment, shows the insert **14** shaped as a hexagon. It should be appreciated that the shape of the inserts **14** may be of many differing kinds including, for example, square, oval, round, and triangular, provided that the openings **20** are accordingly shaped for receiving each of the inserts **14**.

FIG. **4** shows the cellular structure **12** of the armor system **10**. The cellular structure **12** includes, in this embodiment, four openings **20** extending between a first side **16** and a second side **18**. The cellular structure **12** further includes outer walls **46** and inner walls **48**. The outer walls **46** and inner walls **48** have a thickness extending in a direction parallel to axis A and a width **47** extending in a plane perpendicular to axis A. It should be appreciated that both the thickness and the width can be varied throughout the cellular structure **12**. A thickness of approximately 1 inch and a width of 0.25 inches for the outer walls **46**, along with a width of 0.0625 inches for the inner walls **48**, has proven to be acceptable.

The cellular structure **12**, as shown in FIG. **5**, includes a plurality of carbon fiber reinforced polymer fibers **50** continuously extending throughout the cellular structure **12**. It has been found that by placing the fibers **50** continuously throughout both the outer walls **46** and the inner walls **48**, without any break in such fibers **50**, that a high tensile strength is provided to the structure **12** to thereby reduce the lateral displacement of the composite inserts **14**. It has been found that the fibers **50** should be made of a high strength modulus material selected from the group consisting of glass, carbon, and aramid. In the embodiment shown in FIG. **5**, the fibers **50** are shown to extend in a counterclockwise orientation; however, it should be appreciated that the fibers **50** may also extend in other orientations such as a clockwise direction. Further, although not shown in FIG. **5**, it should be appreciated that another embodiment of the cellular structure **12** for use in connection with structures needing less strength, may include the use of fibers continuously extending throughout the outer walls **46** only. In such an embodiment, it is possible that the inner walls **48** may separately have fibers **50** extending continuously throughout the inner walls **48** only.

The present invention **10** is generally shown at **100** in FIG. **6** on a vehicle structure. It should be appreciated that the present invention can be used in connection with many different structures and the example shown in FIG. **6** is only one example of such structures. In FIG. **6**, a cellular structure **102** having a plurality of composite inserts **104** is shown in use with a floor pan **107** of a military vehicle **109**. Although not shown in FIG. **6**, it should be appreciated that several cellular structures **102** could also be assembled adjacent each other and throughout the entire floor pan **107**. In this example, the present invention **100** provides protection against projectile penetration into the floor pan **107** while also providing structural support to the floor pan **107**. It should be appreciated that this example shown in FIG. **6** is only one example provided to demonstrate that the present invention **100** provides both projectile protection for a structure and overall structure support to the same structure.

The present invention **10** is assembled according to the following steps. The cellular structure **12** is provided on a fixture used for holding the structure. The inserts **14** are inserted into the openings **20** of the structure **12** and a filler is applied to the inserts **14** including around at least a portion of the perimeter **25** of the inserts **14**. At least one of the laminate sheets **26**, **28** are applied over the structure **12** having the inserts **14** contained in the openings **20**. A bonding resin is applied to the entire structure **12**, having the inserts **14** in the openings **20** along with the filler and the laminate sheets,

5

thereby created an assembly which is infused together. In the preferred embodiment, the infusing is achieved through the use of a known process referred to as Vacuum Assisted Resin Transfer Molding (VARTM). Although the VARTM infusion process is preferred, it should be appreciated that other methods of infusion may also be used.

The foregoing discussion discloses and describes an exemplary embodiment of the present invention. One skilled in the art will readily recognize from such discussion, and from the accompanying drawings and claims that various changes, modifications and variations can be made therein without departing from the true spirit and fair scope of the invention as defined by the following claims.

What is claimed is:

1. A composite armor comprising: an integrally formed cellular structure having oppositely facing sides and a plurality of openings on at least one of said oppositely facing sides; a plurality of composite inserts received by said plurality of openings; a laminate sheet secured to at least one of the oppositely facing sides of the cellular structure to provide structural reinforcement and contain debris after impact; and wherein the integrally formed cellular structure includes continuously extending fibers, and wherein said continuously extending fibers include individual fibers extending continuously throughout said cellular structure without any break in said fibers.

2. The composite armor as claimed in claim 1, wherein said laminate sheet has an acoustic impedance of between  $0.7 \times 10^6$  and  $40 \times 10^6$  kg/m<sup>2</sup> as measured in a direction parallel to a normal of the laminate sheet.

3. The composite armor as claimed in claim 2, wherein said laminate sheet includes at least two different materials on each of said oppositely facing sides of said cellular structure.

4. The composite armor as claimed in claim 1, wherein said fibers are made of a high modulus strength material selected from the group consisting of glass, carbon, and aramid.

5. The composite armor as claimed in claim 1, wherein said composite insert includes first and second surfaces which are substantially perpendicular to an axis A of said opening.

6. The composite armor as claimed in claim 5, wherein said first and second surfaces include a minimum modulus of  $2.0 \times 10^{10}$  N/m<sup>2</sup> measured in a through thickness orientation.

7. The composite armor as claimed in claim 1, wherein said opening extends between both of said oppositely facing sides.

8. The composite armor as claimed in claim 1, wherein said composite insert includes a plurality of inserts spaced a predetermined distance from each other.

9. The composite armor as claimed in claim 1, wherein said cellular structure includes an exterior wall portion and an interior wall portion.

6

10. The composite armor as claimed in claim 9, wherein said exterior wall portion and said interior wall portion have varying widths.

11. The composite armor as claimed in claim 1, wherein a filler is received in said opening of the cellular structure and adjacent to at least a portion of said composite insert.

12. The composite armor as claimed in claim 1, wherein at least one cellular structure is fixedly attached and made integral with a structure.

13. A composite armor comprising: an integrally formed cellular structure having oppositely facing sides and a plurality of openings on at least one of said oppositely facing sides, wherein said cellular structure is formed from continuous fibers, and wherein said continuous fibers include individual fibers extending continuously throughout said cellular structure without any break in said fibers; at least one composite insert received by said plurality of openings; and a laminate sheet secured to at least one of the oppositely facing sides of the cellular structure to provide structural reinforcement and contain debris after impact.

14. A composite armor comprising:  
an integrally formed cellular structure having outer walls and inner walls having oppositely facing sides and a plurality of openings on at least one of said oppositely facing sides;

at least one composite insert received by said plurality of openings;

a laminate sheet secured to at least one of the oppositely facing sides of the cellular structure to provide structural reinforcement and contain debris after impact; and

wherein at least one of the inner walls and outer walls includes a plurality of continuously extending carbon fiber reinforced polymer fibers and wherein said fibers extend without any break in said fibers.

15. The composite armor as claimed in claim 14, wherein said fibers only extend continuously throughout the outer walls.

16. The composite armor as claimed in claim 14, wherein said fibers extend continuously throughout only the inner walls.

17. The composite armor as claimed in claim 14, wherein said fibers continuously extend throughout both said outer walls and said inner walls.

18. The composite armor as claimed in claim 14, wherein said fibers continuously extend throughout said outer walls and a plurality of separate fibers extend continuously throughout said inner walls.

19. The composite armor as claimed in claim 18, wherein said inner and outer walls are formed together as a single integrally formed cellular structure.

20. The composite armor as claimed in claim 14, wherein said fibers include individual fibers extending continuously throughout said cellular structure.

\* \* \* \* \*